



Surface Performance Ltd
Unit 16 Vicarage Farm
Sunbury On Thames
London
TW16 6DW

0208 2465562
info@surfaceperformance.com
www.surfaceperformance.com

TEST REPORT

Surface Roughness Testing (Laboratory) Performed on a Sample of

ADB60

For:

Ryno Group Ltd

- This report has been prepared by Surface Performance Ltd with all reasonable care, skill and diligence within the terms of the contract with the client. This report is not to be reproduced except in full without prior approval.
- This report is confidential to the client and Surface Performance Ltd accept no responsibility towards any third parties to whom this report is made available to. Any such party relies upon this report at their own risk.
- This report shall not be used for contractual purposes unless signed by the Laboratory or Technical Manager.
- The results given in this report are representative of the sample received only.

REVIEWED & APPROVED BY	SIGNATURE	ISSUE DATE	REPORT NUMBER
Russell Thompson (Technical Manager)		21/08/2025	SP4807B



Surface Performance Ltd
Unit 16 Vicarage Farm
Sunbury On Thames
London
TW16 6DW

0208 2465562
info@surfaceperformance.com
www.surfaceperformance.com

1.0 CONTENTS

Approval Sheet & Preface	Page 1
Contents	Page 2
Introduction	Page 2
Testing Method	Page 2
Location Plans & Requirements	Page 3
Test Results	Page 4
Test Photographs	Page 4
End of Report	Page 5

2.0 INTRODUCTION

Surface Performance Ltd carried out Surface Roughness Testing on Tuesday 19th August 2025 to a sample provided for testing by Ryno Group Ltd, provided with the name ADB60.

The sample was supplied by the client and received at the laboratory on Thursday 14th August 2025 and identified with Surface Performance Ltd sample number SP4807B. The samples are tested as received and the results apply only to the samples tested.

The sample was conditioned for a minimum 24 hours prior to testing at an ambient air temperature of 21-25°C and 40-60% relative humidity in accordance with ISO 291 Class 2 (non tropical countries).

3.0 TESTING METHOD

3.1 Testing was performed in accordance with The UK Slip Resistance Guidelines (UKSRG) 2016 using a Mitutoyo 178-561-02E Surftest SJ-210 Portable Surface Roughness Tester.

3.2 Testing was carried out at 10 x locations in 3 directions, in dry conditions.

3.3 Classification limits are taken from The UKSRG 2016.



4.0 REQUIREMENTS


Classification limits are taken from The UKSRG 2016.

CLASSIFICATION	Rz Microroughness
High Slip Potential	< 10 μm
Moderate Slip Potential	10 - 20 μm
Low Slip Potential	> 20 μm

5.0 LOCATION PLANS

5.1 TEST LOCATION PROXIMITY PLAN

The diagram below identifies the test specimen



6.0 TEST RESULTS

Location 1 - LOW SLIP POTENTIAL

Test Direction	1	2	3	4	5	6	7	8	9	10	Mean Result
A	30.9	20.2	25.4	28.0	22.5	28.3	24.3	24.3	29.7	22.6	25.6
B	29.5	21.8	23.6	24.4	31.8	25.0	26.4	24.3	22.7	23.8	25.3
C	30.2	23.8	26.6	27.5	27.8	25.1	29.6	27.9	25.2	24.0	26.8

7.0 TEST PHOTOGRAPHS



Report Number: SP4807B

Sample: ADB60



Surface Performance Ltd
Unit 16 Vicarage Farm
Sunbury On Thames
London
TW16 6DW

0208 2465562
info@surfaceperformance.com
www.surfaceperformance.com

END OF TEST REPORT

